


Albany Green

granite, from Melocco Stone Pty Ltd





Top: Albany Green quarry. Middle: Aurora Place, Sydney

Dimension Stone is a product of nature and is subject to variation in colour and texture. These images should only be considered as generally representative of the featured stone. Full size slabs are generally available to view on request.

DETAILS

Name:	Albany Green
Substitute Names:	None
Colour & Veining:	Green/Grey With Large Feldspars
Stone Type:	Granodiorite
Quarry Location:	Jerramungup Western Australia
Availability:	Excellent

TYPICAL PHYSICAL PROPERTIES

Bulk Density:	2.72 tonne/m ³
Compressive Strength (dry/wet):	197.3/141.8 MPa
Flexural Strength (dry/wet):	10.9/10.1 MPa
Water Absorption by weight:	0.10%
Abrasion Resistance:	Not Available
Slip Resistance:	Flamed & Blasted: Class V : Very Low risk of slipping

PHYSICAL CHARACTERISTICS

Texture:	Medium Grained
Inclusions:	Minimal
Degree of Polish:	High
Variation of Tonality:	Moderate
Characteristics:	Occasional Flair
Finishes Available:	Polished, Honed, Flamed, Blasted and Satin
Forms Available:	Blocks, Slabs, Pavers, Cobbles and Cut to Size Panels

PETROGRAPHIC ANALYSIS

Plagioclase Feldspar:	58%
Microcline Feldspar:	23%
Quartz:	9%
Biotite Mica:	3%
Opaque Oxide:	2%
Muscovite, Mica & Sericite:	2%
Other Minerals:	1%

Melocco Stone Pty Ltd

Melbourne: 849 Princes Hwy, Springvale, VIC 3171 Australia
Phone: +61 3 9546 0211 **Fax:** +61 3 9547 1105
Email: melocco.vic@melocco-stone.com **Web:** www.melocco.com.au
Sydney: 1 Booth St, Annandale, NSW 2038 Australia
Phone: +61 2 9552 1414 **Fax:** +61 2 9552 1229
Email: melocco.nsw@melocco-stone.com