

Austral Coffee

granite, from AustralAsian Granite Pty Ltd





Austral Coffee

Dimension Stone is a product of nature and is subject to variation in colour and texture. These images should only be considered as generally representative of the featured stone. Full size slabs are generally available to view on request.

DETAILS

Name:	Austral Coffee
Substitute Names:	
Colour & Veining:	Grey / Gold with Brown / Veins
Stone Type:	Gneiss
Quarry Location:	Bruce Rock, Western Australia
Availability:	Good

TYPICAL PHYSICAL PROPERTIES

Bulk Density:	2.62 tonnes/m ³
Compressive Strength (dry/wet):	176/162 MPa
Flexural Strength (dry/wet):	10.9/9.9 MPa
Water Absorption by weight:	0.30%
Abrasion Resistance:	
Slip Resistance:	

PHYSICAL CHARACTERISTICS

Texture:	Fine / Medium Grain
Inclusions:	Heavy Veins
Degree of Polish:	High
Variation of Tonality:	Medium Strong
Characteristics:	Flares and Veins
Finishes Available:	Polished, Honed, Satin, Flamed
Forms Available:	Blocks, Slabs, Tiles, CTS

PETROGRAPHIC ANALYSIS

Plagioclase Feldspar	39%
Microcline Feldspar	30%
Quartz	26%
Biotite Mica	3%
Opaque Oxide	1%
Muscovite Mica & Sericite	1%

AustralAsian Granite Pty Ltd

Adelaide: PO Box 144, Woodville, South Australia 5011 Australia
Phone: +61 8 8243 0055 **Fax:** +61 8 8243 0155
Email: aagranite@aagranite.com.au **Web:** www.aagranite.com.au