


# Austral Juparana

granite, from Melocco Stone Pty Ltd





**DETAILS**

Name:	Austral Juparana
Substitute Names:	Bruce Rock Granite
Colour & Veining:	Yellow/Gold with Brown/Black veins
Stone Type:	Granite Gneiss
Quarry Location:	Bruce Rock, Western Australia
Availability:	Excellent

**TYPICAL PHYSICAL PROPERTIES**

Bulk Density:	2.62 tonnes/m <sup>3</sup>
Compressive Strength (dry/wet):	210.2/192.4 MPa
Flexural Strength (dry/wet):	13.5/12 MPa
Water Absorption by weight:	0.2%
Abrasion Resistance:	65
Slip Resistance:	Flamed & Blasted: Class V : Very Low risk of Slipping Honed: Class X: Moderate risk of Slipping

**PHYSICAL CHARACTERISTICS**

Texture:	Medium grained
Inclusions:	Heavy Veining
Degree of Polish:	High
Variation of Tonality:	Medium
Characteristics:	Flares and veining
Finishes Available:	Polished, Honed, Flamed, Blasted and Satin
Forms Available:	Blocks, Slabs, Pavers, Cobbles and Cut to Size Panels

**PETROGRAPHIC ANALYSIS**

Microline Feldspar:	30%
Plagioclase Feldspar:	30%
Quartz:	26%
Biotite Mica:	3%
Opaque Oxide:	1%
Muscovite, Mica & Sericite:	1%
Alteration Minerals:	<1%

Austral Juparana has been used successfully in many commercial projects such as 126 Phillip St and Cook & Phillip Park as well as finding favour as a striking material for domestic applications.

*Dimension Stone is a product of nature and is subject to variation in colour and texture. These images should only be considered as generally representative of the featured stone. Full size slabs are generally available to view on request.*

**Melocco Stone Pty Ltd**

**Melbourne:** 849 Princes Hwy, Springvale, VIC 3171 Australia  
**Phone:** +61 3 9546 0211 **Fax:** +61 3 9547 1105  
**Email:** melocco.vic@melocco-stone.com **Web:** www.melocco.com.au  
**Sydney:** 1 Booth St, Annandale, NSW 2038 Australia  
**Phone:** +61 2 9552 1414 **Fax:** +61 2 9552 1229  
**Email:** melocco.nsw@melocco-stone.com