


# Balmoral Green

granite, from AustralAsian Granite Pty Ltd







Balmoral Green

*Dimension Stone is a product of nature and is subject to variation in colour and texture. These images should only be considered as generally representative of the featured stone. Full size slabs are generally available to view on request.*

**DETAILS**

|                   |                            |
|-------------------|----------------------------|
| Name:             | Balmoral Green             |
| Substitute Names: | Padthaway Green            |
| Colour & Veining: | Green                      |
| Stone Type:       | Granite                    |
| Quarry Location:  | Padthaway, South Australia |
| Availability:     | Good                       |

**TYPICAL PHYSICAL PROPERTIES**

|                                 |                            |
|---------------------------------|----------------------------|
| Bulk Density:                   | 2.63 tonnes/m <sup>3</sup> |
| Compressive Strength (dry/wet): | 133/121 MPa                |
| Flexural Strength (dry/wet):    | 12.8/12.3 MPa              |
| Water Absorption by weight:     | 0.23%                      |
| Abrasion Resistance:            |                            |
| Slip Resistance:                |                            |

**PHYSICAL CHARACTERISTICS**

|                        |                                  |
|------------------------|----------------------------------|
| Texture:               | Medium Grain                     |
| Inclusions:            | None                             |
| Degree of Polish:      | High                             |
| Variation of Tonality: | Very Minor                       |
| Characteristics:       | Consistent in Colour and Texture |
| Finishes Available:    | Polished, Honed, Satin, Flamed   |
| Forms Available:       | Blocks, Slabs, Tiles, CTS        |

**PETROGRAPHIC ANALYSIS**

|             |     |
|-------------|-----|
| K-Feldspar  | 52% |
| Quartz      | 35% |
| Plagioclase | 10% |
| Hornblende  | 2%  |
| Biotite     | 1%  |

**AustralAsian Granite Pty Ltd**

**Adelaide:** PO Box 144, Woodville, South Australia 5011 Australia  
**Phone:** +61 8 8243 0055 **Fax:** +61 8 8243 0155  
**Email:** aagranite@aagranite.com.au **Web:** www.aagranite.com.au