



# Dreamtime

granite, from Melocco Stone Pty Ltd







Top: Blocks of Dreamtime in the Outback not far from the renowned Devils Marbles (middle).

*Dimension Stone is a product of nature and is subject to variation in colour and texture. These images should only be considered as generally representative of the featured stone. Full size slabs are generally available to view on request.*

**DETAILS**

Name:	Dreamtime
Substitute Names:	Darwin Dreamtime
Colour & Veining:	Red/pink/blue with medium to coarse grains
Stone Type:	Granite Gneiss
Quarry Location:	Tennant Creek Northern Territory
Availability:	Reasonable

**TYPICAL PHYSICAL PROPERTIES**

Bulk Density:	2.65 tonnes/m <sup>3</sup>
Compressive Strength (dry/wet):	147/138 MPa
Flexural Strength (dry/wet):	19/18.7 MPa
Water Absorption by weight:	0.09%
Abrasion Resistance:	Not available
Slip Resistance:	Not available

**PHYSICAL CHARACTERISTICS**

Texture:	Medium to coarse grained
Inclusions:	Occasional veins
Degree of Polish:	High
Variation of Tonality:	Changes in colour between mostly blue to red
Characteristics:	Evenly grained granite with some variation in tone
Finishes Available:	Polished, Honed, Flamed, Blasted and Satin
Forms Available:	Blocks, Slabs, Pavers, Cobbles and Cut to Size Panels

**PETROGRAPHIC ANALYSIS**

Microcline:	60%
Quartz:	30%
Plagioclase Feldspar:	5
Biotite:	3%
Muscovite:	1%
Other Minerals:	>1%

**Melocco Stone Pty Ltd**

**Melbourne:** 849 Princes Hwy, Springvale, VIC 3171 Australia  
**Phone:** +61 3 9546 0211 **Fax:** +61 3 9547 1105  
**Email:** melocco.vic@melocco-stone.com **Web:** www.melocco.com.au  
**Sydney:** 1 Booth St, Annandale, NSW 2038 Australia  
**Phone:** +61 2 9552 1414 **Fax:** +61 2 9552 1229  
**Email:** melocco.nsw@melocco-stone.com